

BindEX™ E-188 Speciality Polymer

TECHNICAL DATA SHEET

BindEX™ E-188 is a maleic anhydride modified linear low density polyethylene adhesive resin. It can be processed within different extrusion and co-extrusion technologies designed to process polyolefins. Due to its high MFI it has easy processability in cast film applications.

Applications

- To adhere LLDPE or LDPE or HDPE and Nylon in multilayer cast films.
- Its high MFI makes it suitable for cast application.
- No dilution is required and should be used 100%.

Key Properties

| General | Typical Value (SI) | Test Method |
|-------------------------|-------------------------|---------------------------|
| MFI (190 °C/2.16 Kg) | 5 g/10min | ASTM D1238 |
| Density | 0.890 g/cm ³ | ASTM D792 |
| Bonded Maleic Anhydride | Low (%) | PLUSS [®] method |

Storage and Handling Procedures

BindEX™ E-188 should be stored in a dry, cool and well-ventilated area protected from UV-light. Improper storage conditions may cause degradation and thus can adversely affect the physical properties of the product.

Processing Conditions

BindEX™ E-188 can be processed on most of the standard extrusion equipments designed to process conventional polyolefins. Maximum processing temperature should not generally exceed 270 °C.

Pluss Advanced Technologies Pvt. Ltd.

610-A Udyog Vihar, Phase V, Gurgaon - 122016 (Haryana), India

Telephone: +91 - 124 - 4309490/91/92

E-mail: info@pluss.co.in | Web: www.pluss.co.in

Packaging

BindEX™ speciality polymers are supplied in pre-dried form in 25 Kg (55 lbs) PE lined, HD woven sack-laminated paper bags and 500 Kg (1102 lbs) FIBC's. Depending upon customer's requirement, the bags can be further palletized for dispatch. They should be stored in cool and dry place.

The information given here is meant as a guide to determining suitability of our products for the stated applications. It is based on trials carried out by our laboratories and data selected from literature and shall in no event be held to constitute or imply any warranty. The products are intended for use in industrial applications. The users should test the materials before use and satisfy themselves with regard to contents and suitability in the desired application. Our formal specifications define the limits of our commitment. Recommendation herein may not be construed as freedom to infringe/operate under any third party patents. In the event of a proven claim, our liability is limited only to replacement of our material and in no case shall we be liable for special, incidental or consequential damages arising out of usage of our material. This datasheet is subject to change without notice.