

## **TECHNICAL DATA SHEET OF savE® HS26N**

## **Technical specification:**

Product	:	savE® HS26N
Description	:	Inorganic phase change material
Appearance	:	Bluish colored liquid with white sediment @25 °C

## Phase transition temperature range and stored thermal energy\*





Temperature vs time curve

Enthalpy vs temperature curve

Property	Value**	Test method	Test conditions (if any)
Phase transition temperature Melting Freezing Nucleation temperature	-26 ℃ -26 ℃ -26 ℃	PLUSS <sup>®</sup> T-History PLUSS <sup>®</sup> T-History PLUSS <sup>®</sup> T-History	<ul> <li>@ -16 °C Liquid bath</li> <li>@ -36 °C Liquid bath</li> <li>@ -36 °C Liquid bath</li> </ul>
Latent heat/enthalpy Liquid Solid	264 kJ/kg 182 kJ/kg	PLUSS <sup>®</sup> T-History PLUSS <sup>®</sup> T-History	@ -29 to -19 ℃ @ -19 to -29 ℃
Density Liquid Solid	1200 kg/m <sup>3</sup> 1122 kg/m <sup>3</sup>	ASTM D891-95 ASTM D891-95	@ 30 °C @ -40 °C
Specific heat Liquid Solid	3.6 kJ/kgK 1.7 kJ/kgK	PLUSS <sup>®</sup> T-History PLUSS <sup>®</sup> T-History	@ 30 °C @ -30 °C
Thermal conductivity Liquid Solid	NA		
Number of cycles tested	~2000	PLUSS <sup>®</sup> Internal	
Maximum operating temperature	90 °C		
Flammability	No		

\* Determined by T-history

\*\*Nominal Valu[es. Actual values mentioned in test certificate.

Compatibility data available on request.

PCM is available in bulk, pouches or in containers of choice (Refer to Document 301\_PCM Encapsulation).

Pluss Advanced Technologies Ltd.

PLUSS-TDS-DOC-026 Version no.-R0, 15-Feb-2022

B-205, Tower B – Pioneer Urban Square, Sec 62, Gurugram-122101, Haryana, India Telephone: +91 - 124 - 4309490/91/92 E-mail: info@pluss.co.in | Web: www.pluss.co

The information given here is meant as a guide to determining suitability of our products for a desired application. It is based on tests carried out by our laboratories and data selected from literature and shall in no event be held to constitute or imply any warranty. The products are intended for use in industrial applications. The users should test the materials before use and satisfy themselves with regard to contents and suitability in the desired application. Our formal specifications define the limits of our commitment. Recommendation herein may not be construed as freedom to infringe/operate under any third party patents. In the event of a proven claim, our liability is limited only to replacement of our material and in no case shall we be liable for special, incidental or consequential damages arising out of usage of our material. This datasheet is subject to change without notice. For detailed safety and handling information regarding these products, please refer to Safety Data Sheet and Bulking handling instruction which is available on request.

