



Tie layer adhesive resin for multilayer lamitubes

PRODUCT APPLICATION NOTES

Pluss Advanced Technologies Pvt. Ltd.

B-205, Tower B – Pioneer Urban Square, Sec 62, Gurugram-122101, Haryana, India

Telephone: +91 - 124 - 4309490/91/92

E-mail: info@pluss.co.in | Web: www.pluss.co.in

Tie Layer Adhesive Resin for Multilayer Lamitubes

Packaging enhances the brand value of any product and a product's success to a great extent depends on its external appearance. Many a time's a consumer's decision is spontaneous and a product moves from the shelf because of attractive packaging. One of the most common yet important class of attractive packaging is Lamitubes.

Multilayer Plastic Laminated Tubes are commonly known as "LAMITUBES". This product is no less than an innovation, which on one hand speaks about the brand through its eye-catching shape & design and on the other hand provides convenience to the consumer.

Lamitubes are made typically from laminates having 5 or 7 layer structure and can be customized in terms of thickness based on specific client requirements and the end packaging application like toothpaste, ointments, cosmetics & ketchups.

One of the most important components in these LAMITUBES is **Tie Layer adhesive resin**. This is used to bond the dissimilar materials together and thus combines the properties of different materials, such as gas barrier resins and moisture barrier resins. The use of this adhesive resin in packaging structures restricts the passage of oxygen, flavor and odor permeation.

Sensing the demand of Tie Layer Adhesive Resin from Lamitube industry, PLUS Polymers has developed a speciality additive marketed under the brand name BindEX E-186, which is used as a tie layer adhesive resin for multilayer laminated structures called Lamitubes.

CHARACTERISTICS OF BindEX E-186

About BindEX E-186

It is a maleic anhydride modified linear low density polyethylene adhesive resin. It is used as a tie layer adhesive resin for bonding dissimilar resins together in increasingly popular multilayer barrier packaging structures called Multilayer Lamitubes. With advanced grafting technology, this grade creates super adhesion to metal, EVOH, PE and PA while maintaining excellent processability.

Properties:

- Appearance : White color granules
- MAH : Medium (%)
- MFI* : 2.0 g/10min
- Density : 0.932 g/cm³

*190 °C/2.16Kg



How does it work?

Maleic Anhydride groups present in BindEX E-186 chemically react with polar which chemically binds aluminum to the polymer chain. Aluminum particles also get embedded into the softer LLDPE layer matrix after corona treatment which results in the continuous lustier of the metalized film.

Suggested Formulation:

BindEX E-186 is used along with other ingredients of Lamitube formulation like PE/PA/Metal, EVOH etc. A typical formulation is as under:

Layer Type	Layer Ratio	Suggested Formulation
Outer Layer	Depending upon the end-	PE/PA/Metal
Adhesive Resin	4%	BindEX E-186
Core Layer	Depending upon the end-	EVOH
Adhesive Layer	4%	BindEX E-186
Inner Layer	Depending upon the end-	PE/PA/Metal

Advantages

BindEX E-186 is developed indigenously for Indian Market. Some of the advantages offered are:

- ✓ Is in synergism with varied flexible film packaging industry requirements.
- ✓ Impart excellent thickness accuracy.
- ✓ Enhanced barrier properties ensuring best shelf life.
- ✓ Ensure better surface finish with crystal clear graphics.
- ✓ Being an olefins adhesive act as a puncture resistant in film.

Processing

The Processing method of the multilayer lamitubes is generally called the co-extrusion method. The resins including the adhesive resin with different properties are pushed into a metal mold by different extruders. Then they are laminated into a tubular shape within the metal mold. As the molding is done in a single step, the stability of the product and production efficiency is quite high.

It is a hygienic process because there is no direct contact with the air outside of the tube.

The information given here is meant as a guide to determining suitability of our products for the stated applications. It is based on trials carried out by our laboratories and data selected from literature and shall in no event be held to constitute or imply any warranty. The products are intended for use in industrial applications. The users should test the materials before use and satisfy themselves with regard to contents and suitability in the desired application. Our formal specifications define the limits of our commitment. Recommendation herein may not be construed as freedom to infringe/operate under any third party patents. In the event of a proven claim, our liability is limited only to replacement of our material and in no case shall we be liable for special, incidental or consequential damages arising out of usage of our material. This datasheet is subject to change without notice.